



Unit 32 Tokenspire Business Park, Hull Road, Woodmansey, Beverley, HU17 0TB • Tel +44 (0)1482 880478 • Fax: +44 (0)1482 880678

Chemical Compatibility of Tapco Roofing Products' Roof Tiles Class A and Class C

Tapco Roofing Products' roof tiles are chemically compatible with most substances and products which are normally present in a roof deck environment. Our roof tiles will not react adversely when exposed to acids, bases and salts. They are also compatible with EPDM, PVC, Uncured Neoprene, and asphalt compounds that are typically present in roofing underlay and self-adhered membranes.

Tapco Roofing Products' Roof Tiles have been tested with the following materials with the result of "no change" to the roof tile samples when immersed for one week with items to follow:

- ✓ Asphalt
- ✓ Oleic Acid (animal fat)
- ✓ Mineral Spirits
- ✓ Mineral Oil
- ✓ Hydrochloric Acid
- ✓ Sulphuric Acid

Although the test results confirm the durable and impermeable characteristics of the Tapco Roofing Products' Roof Tiles, it is not recommended to expose the roof tiles to those substances that would normally not be present on roof deck environments and/or for periods of time beyond the test period (one week).